

CS SPSA S Range is comprised of high quality skived PTFE coated with silicone pressure sensitive adhesive. It provides the unique characteristics of PTFE in a form suitable for application as a surface liner to wood, metal or plastic. A separate liner is applied to the adhesive surface for ease of application.

CS SPSA S liners exhibit excellent release properties and are unaffected by most chemicals and solvents.

Typical Properties	SPSA-3 S	SPSA-5 S	SPSA-10 S	SPSA-20 S	TEST METHOD
Weight (g/m ²)	170	280	540	1080	FTMS 191A-5041
Thickness (mm)	0.080	0.130	0.250	0.500	FTMS 191A-5030
Adhesive Thickness (mm)	0.045	0.045	0.045	0.045	FTMS 191A-5030
Tensile Strength (N/cm)	35	53	96	184	FTMS 191A-5102
Minimum Elongation (%)	200	200	200	200	FTMS 191A-5102
Peel Adhesion (N/cm)	5.4	5.6	5.9	6.8	ASTM D3330-83
Polyken Tack (g)	600	550	420	550	-
Standard Widths (mm)	990	1000	1000	1000	-

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

Ireland

Tel. +353 65 9080170
 Fax. +353 65 9080177
 E-mail: chemfab@saint-gobain.com

Germany

Tel. +49 22 03 956 373
 Fax. +49 22 03 956 421
 E-mail: chemfab@saint-gobain.com

UK

Tel. +44 1706 746900
 Fax. +44 1706 746991
 E-mail: chemfab@saint-gobain.com

Poland

Tel. +48 (63) 261 7252
 Fax. +48 (63) 261 7232
 E-mail: chemfab@saint-gobain.com

www.chemfab.com

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2015 Saint-Gobain Performance Plastics Corporation